

DATA SHEET

Material	ROCKAL Board Insulation (LDB40)
Details	40kg/m³ Density; 50mm Thickness; Non-Faced

ROCKAL Rockwool boards are composed of mineral rock fibers, processed from volcanic basaltic rocks. Fibers are bonded together with a thermosetting binder which gives flexibility and resilience to the product.

It can be used as thermal and acoustical insulation and a fire barrier used in commercial, industrial, and residential buildings.

Description

Thickness (mm)	Density (kg/m³)	Facing	ASTM Classification
50	40	Non-Faced	ASTM C-612

Density	40 (kg/m³)	ASTM C-303
Nominal Thermal Conductivity (@50 °C mean)	0.039 W/mK	ASTM C-767
Thermal Resistance	1.28 M ² .K/W	EN 12667
Service Temp (Hot Side)	400 °C to 750 °C	ASTM C-411
Water Vapor Sorption	<1% (By weight, water repellant, Non- Hygroscopic)	ASTM C-1104
Combustibility	Non Combustible	E-136
Fungi Resistance	Doesn't encourage fungi growth	-
Color	Brown	Visual
Noise Reduction Coefficient (NRC)	≈0.85	ASTM C-423
Corrosiveness	Non-corrosive	ASTM C-692
Flame spread	<10	ASTM E84
Smoked Developed	<25	ASTM E84

Head Office: Al Badr Plaza - Mostafa EL Nahas St.ext-Beside King Fahd Schools - Nasr City-

Cairo, Egypt

Tel & Fax: +(202) 23812796 / 23812804 / 23812795

Factory: El Obour City - Bilbes Road - Kilo 17.5 – Egypt

Tel & Fax: +(202)

Website: www.rockal.org

Branch: Sedey Saaid Sq - Sabtia - Cairo

E-mail: Sales@rockal.org